

MagiCut Process Guidelines

Metallic, Sparkle, Glitter, Foil

- Textile: cotton or cotton/polyester
- Temp: 329-347 F
- Time: 25 seconds
- Pressure: Medium pressure for 10 seconds, allow transfer to cool and peel off backing film. Then place Teflon sheet over garment and press again for 15 seconds.

Flex, Flock

- Textile: cotton or cotton/polyester
- Temp: 360 F
- Time: 10 seconds
- Pressure: medium, peel warm

Reflective

- Textile: cotton or cotton/polyester
- Temp: 300 F
- Time: 10 seconds
- Pressure: low pressure for 10 seconds, peel cool. Cover with sheet of plain paper and press for 5 seconds at maximum pressure.

Glow In The Dark

- Textile: cotton or cotton/polyester
- Temp: 300-365 F
- Time: 8-10 seconds
- Pressure: medium, peel cool